

# Gabbiano Yacht

Clear glossy varnish for wood protection  
in marine environments.



Mod. 51 Rev 64

Last update 30/10/2019

## CHARACTERISTICS:

**GABBIANO YACHT** is a transparent protecting varnish made of urethanes resins, with excellent gloss, great resistance to severe weather conditions, high filling power, to create an elastic, highly adhesive film.

## USE:

**GABBIANO YACHT** is ideal for protecting wood and steel parts of boats, yachts and also ideal for finishing matchboards, frames, doors and chairs even if exposed to marine environment.

## PREPARATION AND APPLICATION:

By brush	Dilute w/	Mineral spirits 5%
By spray	Dilute w/	Mineral spirits 7-10%
By immersion	Dilute w/	Mineral spirits 12-15%
Airbrush	Spray noozle	mm 1,8
	Pressure	Atm 3-4

Apply one or two coats on **XILO-SOL** or directly on wood, properly prepared for painting. It is suggested to apply a fluid first coat to ensure good penetration in the porosity of wood. After 24 hours, sand to remove protruding wood fibres and apply one or two more viscous finishing coats.

Wait 24 hours between coats.

## IMPORTANT NOTES:

- Before applying, make sure the substrate is perfectly dry and cured and well adherent. The surface must be free from dirt, grease, mildew, fungi, bacteria, efflorescence or anything else likely to prevent good adhesion and a successful result.
- Mix the product before use.
- Store in a cool, dry place away from sunlight at a temperature above +5°C.
- Use the product at room and surface temperature between + 5°C and + 35°C and with relative humidity not above 75%
- Avoid drying in environment or surface temperature below + 5°C
- Ensure to have enough coloured product of the same batch in order to complete the job or at least complete portions of it that will avoid drawing attention of differences in hues.
- Wash all tools with mineral spirit immediately after use.

# Gabbiano Yacht

Clear glossy varnish for wood protection  
in marine environments.



Mod. 51 Rev 64

Last update 30/10/2019

## TECHNICAL DATA:

<b>Viscosity ford cup 8</b>	12 ± 2 Sec
<b>Specific weight</b>	0,925 ± 0,030 kg/l
<b>Solids</b>	57 ± 2 %
<b>Spreading rate</b>	12 ± 2 m <sup>2</sup> /l
<b>Appearance of the film</b>	95 ± 96 G (Full Gloss)
<b>Thinner</b>	Mineral spirit
<b>Dust free</b>	1,5-2 hours
<b>Touch free</b>	2 hours
<b>Dry in depth</b>	24 hours
<b>Over painting</b>	24 hours
<b>Packages</b>	2,5 l - 0,750 l
<b>Colours</b>	Transparent glossy

Classification: i/s) High performance monocomponent paints

Limit Phase II (from 01/01/ 2010): 500 g/l

VOC in preparation: < 500 g/l (max).

The above information has been obtained from scrupulously controlled tests, and represents our best and most recent knowledge. This information is provided for reference purposes only. It is not binding upon the manufacturer, and neither may it constitute grounds for any kind of complaint whatsoever associated with the use of the products described, also considering that the conditions of use are beyond our control.

Please refer to the relevant Safety Data Sheet.